

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 0598635115 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) - [www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 - C.F. e P. IVA n. 01592020364

MECCANICA

ECOLOGIA

CERAMICA

AUTOMOTIVE

Modena, 26/02/21

To **AO KERAMOGRANITNIJ ZAVOD**  
STARO-SITNENSKOE SHOSSE  
00000 STUPINO - RUSSIAN (RUS) RU

Attn.

MATERIAL and/or SAMPLE to be tested	Denomination of the Sample	Client Reference – Your delivery	date
Porcelain tiles	SERIE TREVI	Ns ritiro	11/02/2021

Here attached, you will receive the Test Report of Serial No. **20211233**/n, which shows the results of tests required.

**MODENA CENTRO PROVE**

MODENA CENTRO PROVE  
  
Director  
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) -  
[www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 C.F. e P. IVA n. 01592020364



LAB N°1018L

Membro degli Accordi di Mutuo Riconoscimento EA, IAF e ILAC

Signatory of EA, IAF and ILAC Mutual Recognition Agreements

**TEST REPORT: 20211233/1**

Modena, 26/02/21

<b>CUSTOMER</b>	<b>AO KERAMOGRANITNIJ ZAVOD - - STARO-SITNENSKOE SHOSSE - 00000 - STUPINO - RUSSIAN (RUS) - RU</b>
<b>MATERIAL and/o SAMPLE to be tested</b>	Porcelain tiles;
<b>Denomination</b>	SERIE TREVI;
<b>Date of sample reception</b>	11/02/2021;
<b>Date of sample acceptance</b>	11/02/2021;
<b>Kind of test executed</b>	Determination of Water Absorption
<b>Referring standards</b>	UNI EN ISO 10545-3:2000
<b>Shifting from standards</b>	No one
<b>Equipment</b>	Scale cod. MCP C148 - Scale cod. A123 - Ebonorm cod. MCP C68 - Forced ventilation stove cod. MCP C108
<b>Subcontracted phases</b>	No one
<b>Sampling made by</b>	Customer

*The test results reported in this Test Report refer only to the sample sampled by our staff and / or given by the Customer as received.*

*The sample identification data were provided by the customer. Further additional information provided by the Customer will be reported in the Test Report in blue color. If the information provided by the customer influences the validity of the results, MCP declines all responsibility.*

*Any changes / additions made to the Test Report after its first issue will be identified by underlining the text.*

*The Customer undertakes to reproduce this document in its entirety. Any form of partial reproduction is prohibited.*

*The storage times of the samples are indicated on the offer or contract to which this Test Report refers.*

**Examiner**

p.i. Bortolai Alberto

**MODENA CENTRO PROVE**Ceramic Dept. Responsible  
P.I. De Pasquale Roberto**MODENA CENTRO PROVE**Director  
Sant'Unione dr. Giuseppe

**MODENA CENTRO PROVE s.r.l.**

Sede legale e Laboratori: 41123 Modena (Italy) - Via Sallustio, 78  
Tel. 059 822417 r.a. - Fax 059380281 - e-mail : [info@modenacentroprove.it](mailto:info@modenacentroprove.it) -  
[www.modenacentroprove.com](http://www.modenacentroprove.com)  
C.C.I.A.A. Modena n. 228587 - Tribunale di Modena n° 2231 C.F. e P. IVA n. 01592020364



LAB N°1018L

Membro degli Accordi di Mutuo  
Riconoscimento EA, IAF e ILACSignatory of EA, IAF and ILAC Mutual  
Recognition Agreements**DETERMINATION OF WATER ABSORPTION**

Beginning date : 22/02/2021

Analysis ending date : 23/02/2021

**SAMPLE** : Ceramic tiles, marked « **SERIE TREVI** »**RESULTS**

Sample n°	Water Absorption $E_b$ (%)
1	0,09%
2	0,06%
3	0,08%
4	0,09%
5	0,08%
Average value	0,08%

**Examiner**

p.i. Bortolai Alberto

MODENA CENTRO PROVE

Ceramic Dept. Responsible  
P.I. De Pasquale Roberto

MODENA CENTRO PROVE

Director  
Sant'Unione dr. Giuseppe